



TEST REPORT

No.: AJFTS25002141R02_EN

Date: Apr 23,2025

Page 1 of 4

HAINING JINCHAO INDUSTRY CO., LTD

NO.13 JINCHANG ROAD, HAINING ECONOMIC DEVELOPMENT ZONE, HAINING CITY, ZHEJIANG PROVINCE

Sample Description : PE HALOGEN-FREE FLAME RETARDANT TRANSPARENT FABRIC

Style/Item No. : /

The above sample(s) data and information was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Sample Receiving Date : Apr 15,2025

Testing Period : Apr 15,2025 to Apr 22,2025

Test Required : CPAI-84:1995 A specification for flame-resistant materials used in camping tentage, Section 6 Flammability test method, wall & top material.

Test result(s) : See attached sheet

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd Anji Branch

Echo Li
Approved signatory

Scan to see the report



AJFTS25002141R02

Verification:
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

Test Conducted

The test was conducted in accordance with CPAI-84:1995 A specification for flame-resistant materials used in camping tentage, Section 6 Flammability test method, wall & top material.

Test Specimen

Sample description	Fabric
Color	Beige
Fabric weight	110 g/m ²
Size of specimen	300 mm × 70 mm

Conditioning:

[√] 72 Hours Water Leaching;

[√] Accelerated Weathering: Clause 4.2.2.3, UV Fluorescent and Condensation Method, 54 hours accelerated weathering;

Prior to testing, the specimens were conditioned at a temperature of (21±1)°C and a relative humidity of (65±2)% until the moisture equilibrium.

Test Results

[√] As received

Specimen No.	Damaged length (mm)		After-flame (s)		Flaming Broken or Flaming Debris (Yes/No)	
	Lengthwise	Widthwise	Lengthwise	Widthwise	Lengthwise	Widthwise
1	181	180	0	0	No	No
2	186	182	0	0	No	No
3	201	190	0	0	No	No
4	195	184	0	0	No	No
Average	187		0			



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

[√] After leaching

Specimen No.	Damaged length (mm)		After-flame (s)		Flaming Broken or Flaming Debris (Yes/No)	
	Lengthwise	Widthwise	Lengthwise	Widthwise	Lengthwise	Widthwise
1	201	190	0	0	No	No
2	202	191	0	0	No	No
3	191	196	0	0	No	No
4	185	195	0	0	No	No
Average	194		0			

[√] After weathering

Specimen No.	Damaged length (mm)		After-flame (s)		Flaming broken or flaming debris (Yes/No)	
	Lengthwise	Widthwise	Lengthwise	Widthwise	Lengthwise	Widthwise
1	207	191	0	0	No	No
2	189	204	0	0	No	No
3	205	197	0	0	No	No
4	194	198	0	0	No	No
Average	197		0			

Performance Requirements:

1. No specimen from a sample unit of wall and top material shall have an after-flame time of more than 4s; the average after-flame time for all specimens in a sample unit shall not exceed 2s;
2. Portions or residues that break or drip from the test specimens shall not continue to flame after they reach the floor of the test cabinet;
3. These requirements includes:
Specimens that were unleached and unweathered;
Specimens that were leached but unweathered;
Specimens that were weathered but unleached;

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

4. Damaged length, using the procedure described in Sections 6.4.5 and 6.4.6, the maximum permissible damaged for the sample unit and individual specimens shall not exceed the values shown as follows Table.

Roll Material Weight (g/m ²)	Maximum Average Damaged Length for Sample Unit (mm)	Maximum Damaged Length for an Individual Specimen (mm)
[] More than 340	115	255
[] More than 270 but not more than 340	140	255
[] More than 200 but not more than 270	165	255
[] More than 135 but not more than 200	190	255
[✓] More than 50 but not more than 135 *	215*	255*
[] 50 ** or less	230*	255*

*** ALTERNATE PROCEDURE:**

Any wall or top material with a mass of less than 100 g/m² will be considered acceptable if the mass loss during the test is no greater than 5 percent of the original test specimen mass, regardless of the damaged length measurement.

Conclusion: [✓] Pass, [] Fail.

Statement: This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

Photo Appendix:



SGS authenticate the photo on original report only

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com